



Report No: HAPTX22111287

Page 1 of 6

# 检测报告

## Test Report

产品名称 (Sample Name)	01 900D elastic Oxford PU flame retardant coating 02 900D elastic Oxford PU flame retardant coating 03 900D elastic Oxford PU flame retardant coating
委托单位 (Applicant)	Guangzhou Jialong New Materials Co., Ltd
检验类别 (Testing Category)	Delegate testing

江苏环谱检测技术服务有限公司

JIANGSU HAP TESTING SERVICE CO.,LTD



江苏环谱检测技术服务有限公司

JIANGSU HAP TESTING SERVICE CO.,LTD

地址: 扬州市经济技术开发区吴州东路 198 号

Address: NO.198 Wuzhou East Road, economic and technological development zone, YangZhou

URL: [www.hap-test.com](http://www.hap-test.com)

E-mail: [hap@hap-test.com](mailto:hap@hap-test.com)

☎: 400-6600-776

☎: 0514-89711561



# Test Report

Report No: HAPTX22111287

Page 2 of 6

**Applicant** Guangzhou Jialong New Materials Co., Ltd

**Address** No. 106, Fengze East Road, Nansha District, Guangzhou

## Sample Information

No.	Sample Name
01	900D elastic Oxford PU flame retardant coating
02	900D elastic Oxford PU flame retardant coating
03	900D elastic Oxford PU flame retardant coating

\*The information above is provided and confirmed by the applicant.

Sample Received Date Nov.29,2022


Testing Period Nov.29,2022 to Dec.14,2022

**Testing items** Please refer to next page(s)

**Document** ——

**Accordance** ——

**Testing Conclusion** ——

Signer: 





# Test Report

Report No: HAPTX22111287

Page 3 of 6

## 1.Determination of Antibacterial property

**Testing method** Measured according to JIS L 1902-2015. (The strain used in this experiment is Staphylococcus aureus ATCC 6538,sample pretreatment: The sample is cut into 18mmx18mm.Control sample: 100% cotton gauze )

Test microorganisms	Bacterial concentration (CFU/mL)	Bacterial activity value
Staphylococcus aureus ATCC 6538	3.6× 10 <sup>5</sup>	2.79

Note: Sample Test 01 Sample

## 2.Determination of Burning behaviour

**Testing method** With reference to GB/T 5455-2014.(Vertical method, condition B, (105±3)°C, 30min, then cool in the desiccator for no less than 30 minutes)

Testing Item(s)		1	2	3	Average Value
Afterflame time (s)	Weft	0	0	0	0
	Warp	0	0	—	0
Afterglow time (s)	Weft	0	0	0	0
	Warp	0	0	—	0
Damaged length (mm)	Weft	10	10	9	10
	Warp	10	10	—	10
Does it have any drips	Weft	No	No	No	—
	Warp	No	No	—	—
Is the ignited absorbent cotton	Weft	No	No	No	—
	Warp	No	No	—	—
After burning feature	Weft	Contract, curl			
	Warp	Contract, curl			

Note: (1) "—" =Not Regulated  
(2) Sample Test 02 Sample



### 3..Determination of Water resistance (Unit: kPa)

**Testing method** With reference to GB/T 4744-2013. (Test area: 100cm<sup>2</sup>, water pressure rising rate: 6.0kpa /min, test surface: front, sample: apply water pressure below)

Testing Item(s)	03
Water resistance (hydrostatic method)	Group 1:81.04
	Group 2:58.72
	Group 3:55.56
	Group 4:17.48
	Group 5:31.98

Note: (1) The class of hydrostatic resistance and waterproofing performance are evaluated as follows:

Class of resistance to hydrostatic pressure	Hydrostatic pressure value	Waterproofing performance evaluation
Level 0	$P < 4$	Poor hydrostatic performance
Level 1	$4 \leq P < 13$	It has the performance of resisting hydrostatic pressure
Level 2	$13 \leq P < 20$	
Level 3	$20 \leq P < 35$	It has good resistance to hydrostatic pressure
Level 4	$35 \leq P < 50$	It has excellent resistance to hydrostatic pressure
Level 5	$50 \leq P$	

(2) The sample is not uniform and the results are for reference only.

Sample photo:





# Test Report

Report No: HAPTX22111287

Page 5 of 6

Sample photo:



\*\*\*End of report\*\*\*





# Test Report

Report No: HAPTX22111287

Page 6 of 6

## 注意事项

### Notice Items

1、本报告无批准人签字、报告专用章及骑缝章无效。

This report shall be invalid without the signature of the approver, the special seal for the report and the cross-page seal.

2、本报告不得擅自修改、增加或删除。

This report shall not be modified, added or deleted without authorization.

3、报告结果只对本次受检样品负责。若对检测结果有异议，请在报告签发日期后十五天内书面提出，逾期不予受理。

The results of the report are only responsible for the samples tested this time. If there is any objection to the test result, please submit it in writing within fifteen days after the date of issuance of the report. Overdue will not be accepted.

4、未经环谱检测书面同意，不得部分复制本报告，亦不可作为宣传品使用。

Without the written consent of HAP, this report shall not be partially copied or used as publicity materials.

5、当需要结果符合性评价时，若客户无要求，一般不考虑结果的测量不确定度的影响。

When the result conformity evaluation is required, if the customer does not require it, the influence of the measurement uncertainty of the result is generally not considered.

6、此报告无 CMA 标识时，检测数据仅限科研、教学、内部质量控制或研发等活动使用。

When the report has not CMA logo, the test data is limited to scientific research, teaching, internal quality control or research and development activities.

7、本公司出具纸质正版报告与电子数字签名版具备相同效力，当两者内容有差异时以电子数字签名版为准。

The company's paper genuine report has the same legal effect as the electronic digital signature version. When the contents are different, subject to electronic digital signature version.

(具体通用条款详见 <http://www.hap-test.com/company/tytk>)

(For specific general terms, please see <http://www.hap-test.com/company/tytk>)